

Technical Data Sheet

Page 1 of 2

- Properties:** AKEPOX® 1006 is a very fluid, two-component, epoxy resin system with a modified amine hardener which is used for firmly closing cracks and pores. AKEPOX® 1004 is characterized by the following properties:
- hardens relatively quickly
 - has highly penetrative properties on account of its low viscosity
 - very strong colour intensification
 - clear transparent
 - free of solvents
 - weather-resistant
 - good grinding and polishing properties
 - increases the firmness and improves the quality of natural stone surfaces
 - increases the yield and the productivity
 - classification according to the Berufsgenossenschaft der Bauwirtschaft (Accident Prevention and Insurance Association of the German Building Industry): GISCODE: RE 01
- Application Area:** AKEPOX® 1006 is mainly used in the stone-working industry for strengthening porous and fissured natural stone slabs, concrete and concrete ashlar if a very strong colour intensification is required. The hardened product shows a minimal tendency to yellow if exposed to ultraviolet light or to warmth.
- Instructions for Use:**
1. The stone slabs which are to be treated must be pre-calibrated according to their nominal thickness and must be clean and dry.
 2. Four parts by weight of Component A are to be thoroughly mixed with one part by weight of Component B (e.g. 100 g and 25 g) until the mixture is free of streaks. Alternatively, seven parts by volume of Component A are to be mixed with two parts by volume of Component B (e.g. 175 ml and 50 ml); Large amounts can be worked more easily with a dosing and mixing apparatus for AKEPOX® products.
 3. AKEPOX® colouring concentrates or Stone Ink can be used for colouring if required (max. 5%).
 4. The mixture remains workable for approx. 2 hours at 20°C and is applied to the whole surface with a fine-toothed spreader; apply more than once in the event of larger fissures or areas of greater absorption. Cracks which are running completely through the stone are to be closed on the back before application of AKEPOX® 1006.
 5. The surfaces can be ground and polished after approx. 2 days at room temperature. Pre-warmed natural stone slabs can be polished and grind after approx. 3 hours at 60°C and subsequent cooling.
 6. The contact pressure of the grinding and polishing segments should be 1 to 1.5 bar at the most.
 7. Tools can be cleaned with AKEMI® Universal Dilution.
 8. Warmth accelerates and cold retards the hardening process.
 9. Empty the container fully before disposing of it.
- Special Notes:**
- The optimal mechanical and chemical properties can only be attained by adhering to the exact mixing proportions; excess adhesive or hardener has the effect of a plasticizer.

TDS 11.15

Technical Data Sheet

Page 2 of 2

- The colour of the treated surfaces may deepen to a greater or lesser extent depending upon the type of stone involved; a deepening of colour may be more noticeable in the fissured area. Therefore we recommend to test on a sample piece.
- Use separate vessels when component A and B are being extracted from their containers.
- The resin is no longer to be used if it has already thickened or is jellying.
- The best surfaces can only be achieved by using high-quality grinding and polishing segments.
- The product is not to be used at temperatures below 15°C because it will not sufficiently harden.
- The hardened resin can no longer be removed by means of solvents. This can only be achieved mechanically or by applying higher temperatures (> 200°C).
- If the resin has been correctly worked it presents no hazard to health when the hardening process is completed.

Technical Data:

Colour:	light transparent
Density:	comp. A: 1.13 g/cm ³ comp. B: 0.93 g/cm ³
Consumption:	approx. 100 – 200 g/m ²
Working time: at varying temperatures and a quantity of 125 g:	15°C: approx. 3 – 4 hours 20°C: approx. 2 hours 30°C: approx. 1 hour
Hardening times for stone slabs which have been pre-warmed to the given temperatures:	20°C: approx. 2 days 30°C: approx. 1 day

Storage:

2 years approx. under cool conditions in the firmly closed original container.

Health & Safety:

Read Material Safety Data Sheet before handling or using this product.

Important Notice:

The above information is based on the latest stage of development and application technology. Due to a multiplicity of different influencing factors, this information – as well as other oral or written technical advises – must be considered as non-binding hints. The user is obliged in each particular case to conduct performance tests, including but not limited to trials of the product, in an inconspicuous area or fabrication of a sample piece.

TDS 11.15